

Technical Data Sheet Cylinlock[®] 843

July 2012

Page 1 of 1

Product Description

Hernon[®] Cylinlock[®] 843 is a fast curing, high strength anaerobic adhesive yielding higher shear strengths with temperature resistance up to 300°F (149°C) It provides relatively quick cures, outstanding solvent resistance, and improved reliability for metal service applications. Flexible and good for use on Brass.

NSF International

Certified to ANSI/NSF Standard 61 for use in commercial and residential potable water systems

Typical Applications

- Pipe fittings, threaded assemblies
- Bushings
- Pins, wheels, gears, pulleys

Typical Properties (Uncured)

Property	Value
Chemical Type	Methacrylate Ester
Appearance	Green fluorescent liquid
Fluorescence	Positive
Specific Gravity	1.09
Viscosity @ 25°C, cP	2000 - 3000
Flash Point	See MSDS

Typical Properties (Cured)

Property	Value
Fixture time, Brass	1 – 2 minutes
Shear Strength, Grit Blasted Steel	≥ 2000 psi
Torque Strength 3/8 X 16 Steel , Breakaway	250-500 in-lb
Torque Strength 3/8 X 16 Steel , Prevailing	250-500 in-lb
Torque Strength 3/8 X 16 Brass , Breakaway	250-500 in-lb
Torque Strength 3/8 X 16 Brass , Prevailing	250-500 in-lb

Storage

Cylinlock[®] 843 should be stored in a cool, dry location in unopened containers at a temperature between 46°F to 82°F (8°C to 28°C) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused material, do not return any material to its original container.

General Information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

This product is not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). It is recommended to confirm compatibility of the product with such substrates.

Directions For Use

For best results, clean all surfaces with a **Hernon[®]** cleaning solvent Isopropyl Alcohol or acetone and allow to dry.

For Threaded Assemblies the adhesive should be applied to 2-5 threads and the nut screwed on over the adhesive. Allow sufficient time to cure (approx.1 hr). Wipe off excess sealant after nut is applied.

For Slip Fitted Assemblies, apply adhesive around the leading edge of the pin and the inside of the collar and use a rotating motion during assembly to ensure good coverage.

For Press Fitted Assemblies, apply adhesive thoroughly to both surfaces to be bonded and hold together with clamps.

Parts should not be disturbed until sufficient handling strength is achieved.

Disassembly and Cleanup

To aid in disassembly anaerobic compounds can be weakened by heating to at least 500°F (260°C). Once disassembled, cured adhesive can be removed with **Hernon[®] Gasket Remover 30**.

Dispensing Equipment

Hernon[®] offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon[®] Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING[®], INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high performance adhesives and sealants is registered to the ISO 9001:2008 Quality Standard.