

Technical Data Sheet

Silastomer[®] 340

May 2018

Page 1 of 1

Product Description

Hernon[®] Silastomer[®] 340 is a one-component, acetoxo, moisture curing RTV (room temperature vulcanizing) ready-to-use adhesive / sealant and gasketing compound.

Can be used as a form in place gasket material where temperatures may reach up to 600°F. **Silastomer[®] 340** will remain flexible with excellent resistance to aging and vibration.

Meets MIL-A-46106B Type 1 requirements. Also FDA compliant with Regulation Title 21 CFR 175.105 where incidental food contact may be involved.

Typical uses are to replace conventional paper and cork gaskets in:

Automotive

- Valve Covers
- Axle housings
- Water and oil pump seals
- Thermostat housings
- Timing chain covers
- Solenoid covers

Commercial

- Pump and compressor gaskets
- Air conditioning gaskets
- Ductwork gaskets
- Wire and cable insulation

Typical Properties (Uncured)

| Property | Value |
|--|-----------------------------|
| Base | Acetoxo Polysiloxane |
| Color | Red |
| Viscosity | Thixotropic Paste |
| Specific Gravity | 1.18 |
| Extrusion Rate, 1/8 in bead, 90 psi air pressure | 250 gm/min |
| Application Temperature Range (uncured) | 0 to +120°F (-18 to + 50°C) |
| Flash Point | See MSDS |

Directions for Use

Surfaces should be clean and dry. Recommend cleaning surface with a solvent like Mineral Spirits. For gasket applications, apply an even bead to one surface. Surround all bolt holes. Press parts together, and torque normally. On surfaces where adhesion is not required, a light coat of oil or grease will aid in releasing the parts.

Not recommended for cylinder heads, manifolds or in contact with fuels.

To remove – can be wiped off parts before cured. After material cures, abrade or scrape from the surface.

Typical Properties (Cured)

Physical Properties

| Property | Value |
|---|---------------------|
| Gap Cure, in. (mm) | 0.25 (6) |
| Tack Free Time at 77°F, minutes | ≤ 10 |
| Full Cure at 77°F, 0.25 in. bead, hours | 24 |
| Peel Strength Steel, ppi | ≥ 15 |
| Tear Resistance, ASTM D624, Die B | ≥ 50 ppi (2.7 kN/m) |
| Hardness, Shore A | 30 - 35 |
| Tensile Strength at Break, psi | > 300 |
| Elongation, % | 400 |
| Operating Temperature Range short periods, °F | -70 to 600°F |
| Operating Temperature Range continuous, °F | -70 to 500°F |

General Information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Storage

Silastomer[®] 340 should be stored in a cool, dry location in unopened containers at a temperature between 46°F to 85°F unless otherwise labeled. To prevent contamination of unused material, do not return any material to its original container.