

an independent, not-for-profit organization testing for public safety

April 9, 1987

File: MH14222 Project: 86NK30349

Type: R

Hernon Mfg. Inc. Mr. H. Arnon 865 Essex St. Brooklyn, NY 11208

Product:

Pipe Joint Sealing Compounds

The following material resulting from the investigation under the above numbers is enclosed (see attached Addendum for page numbers):

Revised or new pages and illustrations for Follow-Up Service Procedure.

Please file revised pages and illustrations in place of material of like identity. New material should be filed in its proper numerical order.

Please review this material and report any inaccuracies to J. Allen referring to the above project number.

Jeanne Lundsten UNDERWRITERS LABORATORIES INC.

JL: qw PC/Len

Enc: Rpt. and Proc.

cc: New York IC - Proc.

LANCE TO MILE OF THE

Issued: 10-30-86 Revised: 4-9-87

## CONCLUSION

The fire hazard of samples of the products covered by this Report are judged to be small. No flash point in liquid state. "Adhesive/Sealant 427," "920 Pipe Sealant With Teflon," and "940 Pipe Sealant With Teflon" have ignition temperatures of 299°C (570°F), 455°C (851°F) and 447°C (837°F) respectively.

"Adhesive/Sealant 427" and "940 Pipe Sealant With Teflon" \*and "920 Pipe Sealant With Teflon" are suitable for use in devices handling gasoline, potroleum oils, natural gas (pressure not over 300 psig), butane, or propane.

The products are judged to be eligible for Classification and Follow-Up Service. The manufacturer is authorized to use the Laboratories' Classification Marking on such products which comply with the Follow-Up Service Procedure and any other applicable requirements of Underwriters Laboratories Inc. Only those products which properly bear the Laboratories' Classification Marking are considered as Classified by Underwriters Laboratories Inc.

Report by:
J. P. ALLEN
Project Engineer
Casualty and Chemical
Hazards Department

Reviewed by:
R. A, KINGSBURY
Engineering Group Leader
Casualty and Chemical
Hazards Department