

## Test Report 3M 468MP vs HB2135

Test Item:	Test Report		Test Method
Cat No.:	3M 468MP	HB2135 Production no.:60211112	
Printed Krafted Paper	0.110mm*100g/m <sup>2</sup>	100g/m <sup>2</sup>	
Coating thickness (mm)	0.120 ~ 0.125	0.130	-
Adhesion (g/25mm)	2259 ~ 2344	1893 ~ 2056	PSTC-1
Holding Power (1kg/25mm*25mm)	> 48 hrs	> 48 hrs	PSTC-7
Holding Power at 195°C (1kg/25mm*25mm)	NG	> 24 hrs	PSTC-7
Holding Power at 195°C (0.5kg/25mm*25mm)	3 min ↓	> 24 hrs	PSTC-7
Holding Power at 100°C (1kg/25mm*25mm)	> 24 hrs	> 24 hrs	PSTC-7
Initial Tack (cm)	25 ~ 28	12 ~ 12.5	PSTC-6 (#14 Ball)
Remarks	1.Date: Feb. 12, 2008 2.Test condition: 23 ± 5°C ; 55 ± 10% RH 3.Storage condition: 20 ~ 30 °C and avoid exposing to high humidity		